



**Design qualification and  
Type approval of PV modules**

## Overview of IEC 61215 / IEC 61646 tests

Code	Qualification Test	Test Conditions
10.1	Visual Inspection	according defined inspection list
10.2	Performance at STC	cell temperature = 25 °C irradiance = 1000 W/m <sup>2</sup> spectral irradiance distribution according to IEC 60904-3
10.3	Insulation Test	1000 VDC + twice the open circuit voltage of the system at STC for 1 min, leakage current < 50 t.tA, isolation resistance >50 MD at 500 VDC
10.4	Measurement of Temperature Coefficients	Determination of the temperature coefficients of short circuit current and open circuit voltage in a 40°C interval
10.5	Measurement of NOCT	total solar irradiance = 800 W/m <sup>2</sup> spectral irradiance distribution according to IEC 60904-3 wind speed = 1 m/s
10.6	Performance at NOCT	cell temperature = NOCT irradiance = 800 W/m <sup>2</sup> spectral irradiance distribution according to IEC 60904-3
10.7	Performance at low Irradiance	cell temperature = 25°C irradiance = 200 W/m <sup>2</sup> spectral irradiance distribution according to IEC 60904-3
10.8	Outdoor Exposure Test	60 kWh/m <sup>2</sup> solar irradiation
10.9	Hot-Spot Endurance Test	5 one hour exposures to 1000 W/m <sup>2</sup> irradiance in worst-case hot-spot condition
10.10	UV-Exposure according IEC 61345	7,5 kWh/m <sup>2</sup> UV-radiation (280 - 320 nm and 15 kWh/m <sup>2</sup> UV-radiation (280 - 400 nm) at 60°C module temperature
10.11	Thermal Cycling	50 and 200 cycles -40°C to +85°C
10.12	Humidity Freeze Test	10 cycles -40°C to +85°C, 85% RH
10.13	Damp Heat	1000 h at +85°C, 85% RH
10.14	Robustness of Terminations	As in IEC 60068-2-21
10.15	Twist Test	Deformation angle 1.2° over the module diagonal
10.16	Mechanical Load Test	Two cycles of 2400 Pa uniform load, applied for 1 h to front and back surfaces in turn
10.17	Hail Test	25 mm diameter ice ball at 23 m/s, directed at 11 impact locations
10.18*	Light soaking	Light exposure of 800 W/m <sup>2</sup> to 1000 W/m <sup>2</sup> , until Pmax is stable within 2%
10.19*	Annealing	Heat soak at 85 °C until Pmax is stable within 2 %
10.20*	Wet leakage current test	Water spray of terminals and edge immersion with 500 V d.c. applied to determine leakage current

\* Tests only relevant for IEC 61646 qualification

## **Pass criteria**

A module design shall be judged to have passed the qualification tests, and therefore to be IEC type approved, if each sample meets the following criteria:

- The degradation of the maximum power output at standard test conditions (STC) does not exceed 5% after each test nor 8 % after each test sequence;
- The requirements of tests 10.3 (and 10.20) are met;
- No major visible damage (breakage or cracks in cells or glass, detachment of the embedding mass, etc.);
- No sample has exhibited any open circuit or ground fault during the tests;
- For IEC 61646 only: the measured maximum output power after final light-soaking shall not be less than 90% of the minimum value specified by the manufacturer

## **Summary**

The test certificate corresponding to IEC 61215 / IEC 61646 has gained acceptance in the past few years as the quality symbol for PV modules. Nowadays it is required for most national and international funding programs.

An IEC 61215 / IEC 61646 test certificates always refer to the module construction type which has been subjected to the tests. Transferral is only permissible to modules of the same construction type which fulfill the following criteria:

- all materials and module components used are identical
- in the cell connection the same number of less cells are bridged by a bypass-diode.
- the module size and the rated output power do not exceed +10 % of the module type tested.

All PV modules which fulfill these requirements are combined into one PV module type family.

On the basis of the IEC 61215 / IEC 61646 qualification of a PV-module type family, the certificate can be extended to a new module design type through the repetition of certain qualification tests.